



# TECHNICAL PAINT SERVICES

## A146/61 SOLAR REFLECTING ALUMINIUM

**Features:**

A solar reflecting finish, suitable for application to bitumen, concrete and suitably primed steel, providing protection against moisture penetration and overheating of substrate by solar heat. Reflects up to 80% of direct sunlight.

**Availability:**

In 5, 2.5 and 1 Litre containers.

**Volume Solids:**

55% ± 3% (BS 3900 Part A10).

**Preparation:**

The substrate must be thoroughly clean, dry and free from dust and grease. For optimum durability, it is recommended that A146/61 is applied over A146/60 Solar Reflecting Bituminous Heavy Bodied.

**Application:**

Brush, roller, or conventional spray. Thin with X156 White Spirit or ATR154 Synthetic Brushing Thinners if required.

**Note:**

Some difference in brightness and general appearance may be anticipated between brush, roller and spray application, and therefore, mixed methods of application are not recommended.

**Coverage:**

Approximately 50 sq metres per 5 Litres per coat on a non-porous surface at 20 microns dry film thickness.

**Drying:**

Touch dry: 2 hours @ 20°C.

Hard dry & recoatable: 8 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.