



# TECHNICAL PAINT SERVICES

## A148 SWIMMING POOL PAINT

### Features:

A fast drying, Chlorinated Rubber finish which due to its excellent scrub and chemical resistance, is ideally suited to finishing concrete swimming pools and garden ponds. May be applied to concrete that has been newly laid and allowed to weather for 3 - 4 weeks.

### Availability:

5 Litre containers. All BS4800 colours plus Black and White. A non-slip grade is also available.

### Volume Solids:

51% ± 3% (BS 3900 Part A10).

### Preparation:

The substrate must be thoroughly clean, dry and free from dust and grease.

### Application:

Brush or short pile roller. For new concrete, it is recommended that a first coat is applied thinned up to 10% by volume with UTR112 Universal Synthetic Thinners, followed by one or two coats as necessary, unthinned. For fish ponds, it is important that after finishing, the pond is filled, allowed to stand for 10 days, drained and refilled before fish are introduced.

### Coverage:

50 sq metres per 5 Litres per coat.

### Drying:

Touch dry: 30 - 40 minutes @ 20°C.  
3 hours @ 10°C.

Recoatable: 8 hours @ 20°C.  
12 hours @ 10°C.

### Note:

Although water resistant after 2 hours @ 20°C, it is advisable to allow overnight drying before use.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.