



# TECHNICAL PAINT SERVICES

## A36 FLOOR FINISH EPOXY TWO PACK HIGH BUILD

### **Features:**

An extremely hard wearing, two pack floor finish, which has excellent water and wear resistance. Ideal for application to metal and concrete floors. This paint should not be applied over PVA sealer, latex self leveling compound or power floated concrete. Please contact our Technical Department.

### **Availability:**

5 Litre packs containing 4 Litres Base and 1 Litre Catalyst/Hardener in all BS 4800 colours, Black, White and Transparent. A37 Floor Finish Two Pack Epoxy High Build Non-slip also available.

### **Volume Solids:**

58% ± 3% (BS 3900 Part A10).

### **Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Concrete floors must be at least 6 months old before painting. On existing painted floors it is advisable to paint a test patch to check compatibility. For newer concrete, please contact our Technical Department.

### **Application:**

Brush or roller. Mix A36 Floor Finish Two Pack Epoxy base 4 to 1 by volume with AC36/70 Hardener and thin the mixed paint up to 10% by volume with ATR114 Two Pack Epoxy Thinners. Allow to stand for 10 minutes before use. Pot life when mixed: 8 hours @ 20°C.

### **Coverage:**

Approximately 35 sq metres per 5 Litres per coat.

### **Drying:**

Touch dry:	4 hours @ 20°C.
Hard dry:	12 hours @ 20°C.
Full cure:	24 - 48 hours depending on temperature.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.