



# TECHNICAL PAINT SERVICES

## AM60/50 GOLD OR SILVER POWDER IN PHENOLIC TUNG OIL

**Features:**

A pure phenolic wood oil varnish, incorporating metallic powders, affording excellent water resistance and exterior durability. Ideally suited for both interior and exterior decoration.

**Availability:**

5, 2.5 and 1 Litre containers.

**Volume Solids:**

53% ± 3% (BS 3900 Part A10).

**Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease.

**Application:**

By brush or conventional spray. On un-varnished wood (including worn surfaces), apply an initial sealer coat of AP109 Synthamel Undercoat in Yellow or Light Brown thinned up to 20% by volume with X156 White Spirit, followed by one coat un-thinned, before application of AM60/50. If coats are applied at 24 hour intervals, it is not necessary to rub down between coats.

**Coverage:**

Approximately 60 metres per 5 Litres.

**Drying:**

Touch dry: 4 hours @ 20°C.

Hard dry: 8 hours @ 20°C.

Recoatable: Overnight.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.