



TECHNICAL PAINT SERVICES

AP48 LEAD BASED UNDERCOAT

Features:

A special lead based undercoat formulated to optimise the life of A48 Amel Lead Based System. Only to be used on approved surfaces. Lead Regulations apply. In case of any queries please contact our Technical Department prior to purchase.

Availability:

To order only in 5 Litres minimum lots. Colours to complement the A48 Finish.

Volume Solids:

68 % \pm 3% (BS 3900 Part A10).

Preparation:

Use over fresh painted AP48 Lead Based Primer or over cleaned gloss if changing colour.

Application:

Brush only, supplied ready for use. Use X156 White Spirit for cleaning.

Coverage:

Approximately 50 sq metres per 5 Litres depending on the porosity of the Substrate.

Drying:

Touch dry:	Up to 12 hours @ 20°C.
Recoatable:	Minimum 48 hours.
Fully cured:	48 hours.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 0845 230 1244 Fax 0845 230 1255
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.com

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.