



TECHNICAL PAINT SERVICES

APG79 CONTRACT GRADE UNIVERSAL PRIMER

Features:

A fast drying, anti-corrosive, contract grade synthetic primer suitable for direct application to ferrous metals and wood. APG79 Contract Universal Primer may be over-coated with cellulose, single and two pack paint systems and can be forced dried or stoved up to 30 minutes @ 120°C.

Availability:

Red Oxide, Grey, White and Black, in 5 Litre containers. Other colours made to order, subject to minimum orders.

Volume Solids:

55% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Aluminium, alloys or galvanised surfaces should be treated with UP89/25 Two Pack Etching Primer prior to application of APG79.

Application:

By brush, roller or conventional spray. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 40 - 50 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry:	15 - 20 minutes @ 20°C.
Hard dry:	30 minutes - 1 hour @ 20°C.
Recoatable:	1 hour @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.