



# TECHNICAL PAINT SERVICES

## B2/10 DRINKING WATER TANK BLACK

### **Features:**

A non-toxic coating with good resistance to sulphates, acids and alkalis, which is suitable for application to concrete and metal reservoirs and water towers conforming to BS 3416 Type II, and therefore suitable for use on drinking (potable) water tanks and associated pipework.

### **Availability:**

5, 2.5 and 1 Litre containers.

### **Volume Solids:**

55% ± 2% (BS 3900 Part A10).

### **Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Previously painted surfaces should be de-rusted and all exposed metal surfaces treated with AP79 Universal Primer.

### **Application:**

Brush, spray or dipping. On concrete, which must be at least 6 months old, a minimum of three coats should be applied, allowing 16 hours drying between each coat. On metal, a minimum of two coats should be applied. Thinning is not normally necessary, but brushes etc. should be cleaned with X156 White Spirit.

### **Coverage:**

Approximately 8 - 15 sq metres per Litre to achieve a dry film thickness of 35 microns, depending on porosity of substrate.

### **Drying:**

Touch dry: 2 hours.  
Recoatable & hard dry: 16 hours @ 20°C.

### **Note:**

For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

**FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.**