



# TECHNICAL PAINT SERVICES

## FL42/70/1 FLUORESCENT OVERCOAT CLEAR VARNISH

**Features:**

A durable, water white clear varnish for use over F42 Fluorescent Finish as a protective coating to delay colour degradation.

**Availability:**

5, 2.5 and 1 Litre containers.

**Volume Solids:**

45% ± 3% (BS 3900 Part A10).

**Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease.

**Application:**

Conventional spray or dipping. Thin up to 25% by volume with FTR42 Fluorescent Thinners to achieve a viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

**Coverage:**

Approximately 60 sq metres per 5 Litres @ 25 microns dry film thickness.

**Drying:**

Touch dry: 30 minutes @ 20°C.

Hard dry: 1 hour @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.