



TECHNICAL PAINT SERVICES

H44/10/1 HEAT RESISTING HIGH TEMPERATURE GLOSS BLACK

Features:

A relatively inexpensive gloss black which is suitable for direct application to mild steel and is heat resistant up to 200°C. Exterior exposure will lead to a loss of gloss after 4 - 6 weeks.

Availability:

5, 2.5 and 1 Litre containers.

Volume Solids:

55% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease.

Application:

Do not apply to heated surfaces, cool before applying by brush or conventional spray. A minimum of two coats should be applied. Supplied ready for use. Use X156 White Spirit for cleaning.

Coverage:

Approximately 50 sq metres per 5 Litres @ 35 microns dry film thickness.

Drying:

Touch dry: 2 hours @ 20°C.

Hard dry & recoatable: 16 hour @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.