



# TECHNICAL PAINT SERVICES

## R1007 ACRYLATED RUBBER FINISH

### **Features:**

A fast drying, single pack finish, which has mild resistance to a wide range of chemicals, including acids, alkalis, inorganic salts, mineral oil and water. Ideally suited for application to general industrial situations, plant and moist conditions and can be used on wood and on various metals via a suitable primer.

### **Availability:**

BS4800 colour range made to order in 5 and 2.5 Litre containers. A limited range of RAL colours can be made to order, minimum 5 Litre lots. RP 1007 Acrylated Rubber Primer and Undercoat also available.

### **Volume Solids:**

51% ± 3% (BS 3900 Part A10).

### **Preparation:**

The surface should be clean, dry and free from dust and grease.

### **Application:**

Brush, roller or airless spray. Supplied ready for use for brushing. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a suitable spraying viscosity. We recommend a 1.9 Thou' airless tip size at 2000psi. R1007 may be applied over previously coated surfaces of itself or over RP1007 Acrylated Rubber Undercoat or RP1007 Primer.

### **Coverage:**

40 - 50 sq metres per 5 Litres @ 25 microns dry film thickness.

### **Drying:**

Touch dry:	1 hour @ 20°C. 3 hours @ 10°C.
Recoatable:	8 hours @ 20°C. 12 hours @ 10°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

**FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.**