



# TECHNICAL PAINT SERVICES

## RP10 CHLORINATED RUBBER ZINC PHOSPHATE PRIMER

### **Features:**

A fast drying Chlorinated Rubber based primer, pigmented with Zinc Phosphate, affording good abrasion resistance and anti-corrosive properties. Ideal for ferrous & non-ferrous metals including aluminium & galvanised surfaces. Also suitable for use as a primer for newly plastered walls or dry lining. Forms an ideal base for R10 Chlorinated Rubber Paint. See Preparation below.

### **Availability:**

Grey & Light Cream in 5 Litre containers. Other colours to order.

### **Volume Solids:**

50% ± 3% (BS 3900 Part A10).

### **Preparation:**

The surface should be clean, dry and free from corrosion, dust and grease. Prior to application of RP10, aluminium should be coated with UP89 Two Pack Etching Primer and galvanised metal should be treated with X85 Mordant Solution. For plastic use PP129 Adhesion Promoter.

### **Application:**

Brush, conventional or airless spray. Supplied ready for use for brushing. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C. We recommend a 1.9 Thou' airless tip size at 2000psi. For new plaster thin by 15% by volume.

### **Coverage:**

40 sq metres per 5 Litres giving a dry film thickness of 50 microns.

### **Drying:**

Touch dry: 30 - 40 minutes @ 20°C.  
Recoating time: Minimum of 8 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

**FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.**